



Rekortan[®]



APT
POWERED BY *SPEED.*

SYNTHETIC TRACK SURFACING- REKORTAN[®] R10 FULL POUR SPECIFICATION

PART 1- GENERAL

1.01 SUMMARY

- A. The contract work to be performed under this section consist of furnishing all required labor, materials, equipment, implements, parts and supplies necessary for, the surfacing in accordance with these specifications and indicated on the drawings.
 - 1. Rekortan[®] R10 Full Pour- A 2-layer, 10mm impermeable full pour track system. It consists of a self-leveling base coat, and a flood and chip top coat of polyurethane and embedded EPDM rubber granules. The minimum depth of the system shall be 10mm with the depth of the top-wearing layer a minimum of 5mm.

1.02 CODES AND STANDARDS

- A. Codes and standards follow the current guidelines set forth by the International Associations of Athletics Federations (IAAF), the National Collegiate Athletic Association (NCAA) and the National Federation of State High School Associations (NFHS).

1.03 SUBMITTALS AND SUBSTITUTIONS

- A. Request for deviations or substitutions from the specifications must be made in writing seven days prior to the bid date. Complete product data including specifications, application rates, mixing instructions and a sample shall be sent with the request to the District and/or its agent for an evaluation. Alternatives will be allowed only by addendum.
 - 1. Submit three (3) sets of manufacturer's product data sheets including installation guidelines and maintenance guidelines.
 - 2. Submit three (3) representative track samples in the color of surfacing to be installed.

REKORTAN

- 
3. Submit Material Safety Data Sheets (MSDS) or Safety Data Sheets (SDS) for all individual components of the product being installed
4. Submit evidence that the synthetic surfacing contractor is a member of the American Sports Builders Association (ASBA).

1.04 QUALITY ASSURANCE

- A. The track surfacing installer shall be authorized by APT and possess a minimum of ten (10) years' experience installing the specified system.
- B. The supervisor of the installing company must have ten (10) years' experience in surfacing with the specified polyurethane system. A letter of certification must accompany the bid proposal.
- C. The manufacturer (APT) must represent a minimum of four (4) IAAF track systems.
- D. All material components must be procured and manufactured from APT, a single source. No substitutes allowed.
- E. All polyurethanes used must be manufactured by APT an ISO 9001 and ISO 14001 Certified Company. Manufacturer's ISO 9001 and ISO 14001 Certificate must accompany bid.**

1.05 SITE CONDITIONS

- A. Weather: Surfacing shall not begin if rain is imminent, if gusting winds are occurring or when the threat of freezing exists within 24 hours.
- B. Site: During any surfacing and striping, sprinkler systems must be shut off or controlled so that no water falls on the track or event area surfaces. Other trades and school district personnel must stay off the wet or curing surface.
- C. Only mix and apply when meeting manufactures recommended guidelines.



APT

109 Conica Lane
P.O. Box 160
Harmony, PA 16037 USA

Phone: 724.452.1330

Fax: 724.452.1703

Web: sportsbyapt.com

- 
- D. The General Contractor shall provide temporary barriers as required to prevent public entry to construction area and to protect adjacent properties from damage during construction operation.

1.06 WARRANTY

- A. Provide manufacturers standard five (5) year warranty

PART 2- PRODUCTS

2.01 SUPPLIER

- A. Advanced Polymer Technology/Manufacturer
109 Conica Lane / PO BOX 160
Harmony, PA 16037
724-452-1330

2.02 MATERIALS

- A. Rekortan® R10 Track Surface: Full pour, layered Qualipur polyurethane bound track surface with an embedded EPDM broadcast rubber finish.

Materials include:

1. Qualipur Primer
2. SBR Broadcast Rubber
3. Two-Component Qualipur Polyurethane
4. Melos colored EPDM Broadcast Rubber

PART 3- EXECUTION

3.01 EXAMINATION

- A. The General Contractor shall verify that all asphalt / concrete paving meets all dimensional accuracy, strength, and surface preparation. Notify owner of any deficiencies. Recommended compaction of asphalt and sub base is 95%.



APT

109 Conica Lane
P.O. Box 160
Harmony, PA 16037 USA

Phone: 724.452.1330

Fax: 724.452.1703

Web: sportsbyapt.com

- 
- B. The General Contractor shall verify that all concrete work meets all required tolerances. Notify owner of any deficiencies.
- C. Upon Completion of paving, it is the responsibility of the paving contractor to water flood the surface with the use of a water truck. If after 30 minutes on a 70° F day, 'bird bathes' are evident in a depth more than 1/8" the paving contractor, track surfacing contractor and the owner's representative will determine the best method of correction.
- D. Entire surface shall be clean and free of all dirt, oil, grease or any other foreign residue. It is the responsibility of the General Contractor to ensure that the surface is thoroughly clean in all areas of the new and/or existing asphalt or concrete base as necessary to ensure adhesion of the track.
- E. Minimum curing time for base prior to beginning of surfacing is 14 days for new asphalt paving and 28 days for new concrete. No concrete curing compounds are allowed.
- F. Beginning installation stipulates track installer "accepts" existing conditions. Adhesion to the existing asphalt is the surfacing contractor's responsibility.

3.02 PRODUCT AND MATERIAL DESCRIPTION

- A. Rekortan® R10 is a 2-layer, 10 mm, impermeable full pour system, consisting of a base layer with SBR rubber, and a flood and chip topcoat of Qualipur polyurethane and embedded EPDM broadcast rubber granules.
- B. Rubber (Black SBR Broadcast): The rubber in the base layer shall be specifically graded Styrene Butadiene Rubber (SBR). SBR is to be dried to no less than 2.5% moisture and sealed in bags.
- C. Colored Rubber (EPDM Broadcast): Must be Melos rubber. Unless specified black rubber is not allowed in the wearing course. Color: Red unless otherwise specified.



APT

109 Conica Lane
P.O. Box 160
Harmony, PA 16037 USA

Phone: 724.452.1330

Fax: 724.452.1703

Web: sportsbyapt.com

- 
- D. Full Pour Polyurethane: The 2 layers of full pour polyurethane shall be made of a two-component Qualipur polyurethane compounded with no solvents or fillers added. The specified products are Qualipur 5050 (A & B) in the base and top layers.

3.03 APPLICATIONS PROCEDURES

- A. The entire surface shall be clean and free of dirt, oil, grease or any other matter upon arrival of the installation team. Any dirt, etc. shall be pressure washed off the base by the general contractor.
- B. Prime entire surface area with a compatible Qualipur polyurethane primer. Mask and protect adjacent structures, as required. Primer shall dry to a tack free condition, but no longer than 24 hours, before the application of the base layer. The consumption rate is 0.29 lbs/sy (0.16 kgs/sm).
- C. Base Layer: After the primer and/or any detail applications have cured to tack-free, but no longer than 24 hours, apply the mixed Qualipur 5050 coating, using a notched trowel or squeegee to achieve an even wet look. Do not overwork the material this can cause excessive trapped air. The consumption rate the of Qualipur 5050 is 6.64 lbs/sy (3.60 kgs/sm). Broadcast to excess with Black SBR rubber, using a flat shovel or machine spreader ensuring all of the coating is covered. The consumption rate for the SBR rubber is 9.22 lbs/sy (5.00 kgs/sm).
- D. Top Layer: After the base layer has cured, but not longer than 24 hours, remove any rubber that is not bonded to the coating using a sweeper and/or vacuum/blower. Mix the Qualipur 5050 coating and apply using a notched trowel or squeegee, to achieve an even wet coat. The consumption rate for Qualipur 5050 is 6.64 lbs/sy (3.60 kgs/sm). Broadcast to excess with 1-4mm colored EPDM granules, using a flat shovel or machine spreader ensuring all of the coating is covered. The consumption rate for the EPDM granules is 9.22 lbs/sy (5.00 kgs/sm).
- E. Allow top layer to cure, and reclaim all excess rubber by means of a mechanical sweeper.



APT

109 Conica Lane
P.O. Box 160
Harmony, PA 16037 USA

Phone: 724.452.1330

Fax: 724.452.1703

Web: sportsbyapt.com



REKORTAN

3.04 STRIPING

- A. All line marking paint is to be compatible and approved for the synthetic surfacing. Only an experienced track striping specialist shall perform the striping.

END OF SPECIFICATION - REKORTAN® R10

Rev 2 GT 06/17/14



APT

109 Conica Lane
P.O. Box 160
Harmony, PA 16037 USA

Phone: 724.452.1330
Fax: 724.452.1703

Web: sportsbyapt.com